



Hot saving: Cold phosphating

SURFACOTE® 240

Low-temperature zinc phosphating
(nickel-free)



**KIESOW
DR. BRINKMANN**

Characteristics

- » Produces even at low temperatures uniform, finely crystalline zinc phosphate layers
- » Excellent adhesion base for subsequent lacquering and powder coating
- » Easy to handle
- » Nickel-free

Application

- » 27 – 45 °C immersion process
35 – 45 °C spray process
- » Steel and zinc material

Layer Formation

- » Fine crystalline
- » Weight of coating: 3.8 – 4.8 g/m²
(immersion process)
1.7 – 2.5 g/m²
(spray process)

www.kiesow.org

KIESOW DR. BRINKMANN GmbH & Co. KG

D-32758 Detmold · Germany

Wittekindstraße 27–35

Phone: +49 (52 31) 76 04-0

Fax: +49 (52 31) 76 04-28

E-mail: vertrieb@kiesow.org

D-12057 Berlin · Germany

Boschweg 4

Phone: +49 (52 31) 76 04-0

Fax: +49 (52 31) 76 04-661

E-mail: kiesow.berlin@kiesow.org